



BOAI NKY

PolyViscol® & OraRez®
Polymers for Personal Care & Oral care



Hair Care



Skin Care



Oral Care



BOAI NKY PHARMACEUTICALS LTD.

Contents

3.About US ■

5.PolyViscol[®] K ■

7.PolyViscol[®] VA ■

9.OraRez[®] W ■

11.OraRez[®] MS ■

12.KoVidone[®] I ■


13.WhiVidone[®] ■



Polymers for Personal and Oral Care

PVP K series

Trade Name:	PolyViscol® K
INCI/CTFA Name:	Polyvinylpyrrolidone
Description:	Homopolymer of Vinylpyrrolidone
Monomer unit molar mass:	111.14g/mol
CAS-No. :	9003-39-8



Properties:

Clear aqueous solutions obtained for all concentration levels; Polymers are non-ionic, neutralization not required; Capable of stabilizing suspensions, emulsions and dispersions; High compatibility with inorganic salts, many resins and other cosmetic raw ingredients; Resultant films have high capacity for water absorption.

Specification:

Products	Appearance	Mv	K Value	Main applications
PolyViscol® K12	Powder	2500	10-15	Solubilizer/dispersant for pigments in cosmetics
PolyViscol® K15	Powder	8000	13-18	
PolyViscol® K17	Powder	10000	15-19	
PolyViscol® K30	Powder	60000	27-32	Hair sprays, hair gels, skin care creams
PolyViscol® K30L	30% aqueous solution	60000	27-32	
PolyViscol® K60	Powder	380000	55-65	Hair gels, facial masks
PolyViscol® K60L	40% aqueous solution	380000	55-65	
PolyViscol® K85L	20% aqueous solution	950000	76-89	
PolyViscol® K90	Powder	1300000	88-96	Hair gels
PolyViscol® K90L	20% aqueous solution	1300000	90-100	
PolyViscol® K120	Powder	3000000	105-130	Strong hold hair gel
PolyViscol® K120L	11% aqueous solution	3000000	105-130	

Applications:

Film former and thickener for hair styling products, e.g. hair gels, mousses, pump sprays; Emulsion stabilizer in creams and lotions; Dispersant for hair colorants; Foam stabilizer; Destainer and gelling agent in toothpastes; Thickening agents for oral and optical preparations.

PolyViscol® K series products are used extensively in a wide range of applications in hair care, skin care and oral care products. The products are used in formulations where viscosity modification and film forming properties are required. PolyViscol® K series are particularly well suited for use in hair styling products; especially clear hydro or hydro-alcoholic formulations. Typical examples include the following applications.

- Hair gels; • Hair mousses; • Liquid hair setting preparations; • Pump sprays

Hair styling formulations containing 3-5% of PolyViscol® K30 result in medium hold products, while concentrations of 7-9% result in strong hold styling products (Figure 1).




Figure 1: Curl retention comparison for varying concentrations of PolyViscol® K30 solutions at 30 ° C and 60% RH.

Hair styling formulations containing 3% or more PolyViscol® K90 result in strong hold styling products (Figure 2). The use of PolyViscol® K90 also reduces the brittleness of the resultant hair styling film making the resultant film more durable.




Figure 2: Curl retention comparison for varying concentrations of PolyViscol® K90 solutions at 30 ° C and 60% RH.

Classic hair styling gel containing PolyViscol® K90 & K30 No. H-AR-2010003


	%	Ingredient	Supplier
A	0.50	Carbopol® 980	Noveon
	49.50	Deionized water	
B	0.40	Aminomethyl propanol	
C	10.00	PolyViscol® K90L 20% aqueous solution	NKY
	10.00	PolyViscol® K30L 30% aqueous solution	NKY
	0.10	Disodium EDTA	
	q.s	Perfume	
	q.s	PEG-40-Hydrogenated Castor Oil	
	q.s	Preservative	
	29.2	Deionized water	



Polymers for Personal and Oral Care

PVP/VA

Trade Name: PolyViscol® VA
INCI/CTFA Name: VP/ VA Copolymer
Chemical description: Copolymer of Vinylpyrrolidone/Vinyl acetate
Monomer unit molar mass: VP - 111.14g/mol VA - 86.09g/mol
CAS-No. : 25086-89-9



Properties:

Aqueous solutions are non-ionic, neutralization not required; Resultant films are hard, glossy, and water-removable; Tunable viscosity, softening point and water sensitivity depending on VP/VA ratio; Good compatibility with many modifiers, plasticizers, spray propellants and other cosmetic ingredients.

Specification:

PolyViscol®	Appearance	K Value	VP/VA ratio	Application
VA37E	Ethanol solution	26-38	30/70	Ethanol-based hair sprays and mousses
VA55E	Ethanol solution	26-38	50/50	
VA64E	Ethanol solution	26-34	60/40	
VA64W	Aqueous solution	26-34	60/40	Water-based hair gels, mousses and sprays; facial masks; cosmetics
VA64	Powder	26-34	60/40	
VA73E	Ethanol solution	26-38	70/30	Hair gel and mousse
VA73W	Aqueous solution	26-34	70/30	Hair gels and mousses; facial masks

Applications:

Film-forming agents and fixatives in hair care products, e.g. hair styling sprays and pumps, hair gels, styling lotions and mousses. Film-forming agents in skin care products, e.g. facial masks.

PolyViscol® VA series copolymers are an excellent choice for film forming and hair-fixing agents. The incorporation level of vinyl acetate can adjust copolymer properties to give films having varying flexibility and water sensitivity. This tunable composition allows PolyViscol® VA copolymers to be used over a broad range of hair products including: hair sprays, gels, mousses and setting lotions.

Hair styling formulations containing more than 3% PolyViscol® VA64 result in strong hold styling products (Figure 3).




Figure 3: Curl retention comparison for varying concentrations of PolyViscol® VA64 solutions at 30 °C and 60% RH.

Increased incorporation levels of VA units in PolyViscol® VA copolymers has a significant effect of reducing the moisture uptake of resultant films (Figure 4). This results in an improvement of the high humidity curl retention and reduced tack for resultant hair styling products. The films containing higher levels of VA units also possess a more natural/soft feel on the hair. Increasing VA levels also increase the polymer's hydrocarbon compatibility for application in hair sprays using hydrocarbon propellants.




Figure 4: Water absorption at varying humidity levels for various PolyViscol® VA films and PolyViscol® K30 film at 25 °C.

Regular Hold Styling Gel with PolyViscol® VA64 No.H-AR-2010001

	%	Ingredient	Supplier
A	0.50	Carbopol® 980	Noveon
	40.00	Deionized water	
B	0.70	Triethanolamine	
C	3.00	PolyViscol® VA64 powder	NKY
	0.10	Disodium EDTA	
	q.s	Perfume	
	1.50	PEG-40-Hydrogenated Castor Oil	
	q.s	Preservative	
	54.2	Deionized water	




Polymers for Personal and Oral Care



PVM/MA Diacid

Trade Name: OraRez® W
 Chemical description: Free acid of the copolymer of methyl vinyl ether-co-maleic anhydride
 CAS No. : 25153-40-6



Properties:

Soluble in water and alcohols; Excellent wet adhesive strength; Bioadhesive; Strong chelating/complexing properties; Solution and film properties adjustable via carboxylic acid neutralization/reaction.

Specifications :

OraRez®W	20P	100P
Appearance	White to off-white powder	
PH (5% in aq. soln.)	1.5-2.5	1.5-2.5
Moisture%max	6.0	6.0
Specific viscosity SV (1% aq. soln.)	0.4-1.5	4.0-10.0
Heavy metals ppm max.	10	10

Application:

Oral Care: OraRez® W serves as a mucosal/dental adhesive resin for toothpastes and mouth washes providing long-lasting tartar control in combination with fluoride and pyrophosphate. Enhanced mucosal retention and delivery of drugs and actives. Active solubilizer. Buccal adhesive.

Skin Care: Bioadhesives, moisturization, active delivery, hydrogels, film former, chelator.



Oral Care:

OraRez® W forms protective films on teeth surfaces that resist erosion from saliva and acidic beverages. Dental tubes can be effectively protected to reduce dentinal hypersensitivity (Clin Oral Invest (2013) 17: 775-783).

The addition of OraRez® W to toothpaste and mouth wash products can increase the effectiveness of active retention in the oral cavity to make products more efficacious at reducing both plaque and tartar formation (J Clin Dent, 2010, 21 [Spec Iss] 93-123).

The strong complexing and film properties of OraRez® W is an important ingredient in oral formulations focused on reducing dental caries. A combination of OraRez® W/pyrophosphate/sodium fluoride is able to dissolve tartar seeds before they can grow into tartar crystals (US patent 4,183,914).

The excellent mucosal adhesive properties of OraRez® W makes it an excellent ingredient choice for buccal adhesive and mucosal delivery systems.



Skin care:

OraRez® W when used in the combination with such ingredients as: glycerin, glyceryl acrylate/ acrylic acid copolymers, propylene glycol can be the basis for moisture enhancing formulations. Resultant systems show excellent lubricity and impart a silky after-feel to skin creams and lotions.

The bioadhesive properties of OraRez® W makes it an excellent choice for the development of bandage adhesives (skin friendly) and hydrogels for wound care and active delivery.

The unique polyelectrolyte structure and binding properties of OraRez® W makes it an excellent choice for developing new advances in biomedical and skin care formulations focused on: drug transport systems, enzyme mobilization, nucleic acid and protein binding and “smart” active delivery systems.





Polymers for Personal and Oral Care




PVM/MA MS

Trade Name: OraRez® MS

Chemical description: Mixed calcium/sodium salt of methyl vinyl ether-co-maleic acid copolymer

CAS-No. : 62386-95-2



Properties:

Water soluble polymer; Excellent wet adhesive strength; Strong cohesive forces due to calcium bridges; Excellent mucosal adhesive; Highly viscous aqueous solutions; Low toxicity.


Specification:

OraRez® MS	Specification
Appearance	Free flowing white or off-white powder
pH(1% in water solution)	6.0~7.0
Moisture (%max)	10
Calcium (%)	11~16
Tap density (g/cm ³)	≥ 0.5
Total bacteria count (CFU/g)	≤ 500
Yeast/mold (CFU/g)	≤ 200
E.coli (CFU/g)	Negative
Staphylococcus aureus (CFU/g)	Negative
Salmonella (CFU/g)	Negative

Application:

OraRez® MS is an outstanding oral mucosal adhesive suitable for denture adhesive formulations. The ionic bridges inside the OraRez® MS molecule results in both adhesive and cohesive adhesion to generate long lasting and durable oral denture adhesive systems. OraRez® MS acts as an adhesive cushion between the denture and gums to strongly adhere the denture to the gums and reduce the likelihood for irritation due to a loose fitting denture. The use of OraRez® MS based denture adhesives is an essential component for obtaining natural and comfortable feeling dentures.

Trade Name :	KoVidone® -I
INCI/CTFA Name :	PVP-Iodine
Chemical description :	Complex of Polyvinylpyrrolidone with Iodine
Synonyms:	PVP-Iodine, Povidone Iodine, Povidone Iodinated, Polyvinylpyrrolidone-iodine complex, PVP-I
CAS-No. :	25655-41-8
Pharmacopeia Monographs:	Conforms to current USP/NF, Ph. Eur.



Properties:

Broad spectrum biocide; Water soluble, also soluble in: ethyl alcohol, isopropyl alcohol, glycols, glycerin, acetone, polyethylene glycol; Film-forming; Stable complex; Less irritating to skin and mucosa; Non-selective germicidal action; No tendency for generating bacterial resistance.

Specification :

KoVidone®-I	CP	USP	EP
Appearance	Free-flowing, reddish-brown powder		
Available Iodine (%)	9.0-12.0	9.0-12.0	9.0-12.0
Iodine (% maximum)	6.6	6.6	6
Heavy Metals (ppm maximum)	20	20	--
Ash (% maximum)	0.1	0.025	0.1
Nitrogen Content (%)	9.5-11.5	9.5-11.5	--
pH Value (10% aqueous soln.)	-	--	1.5-5.0
Loss on Drying (% maximum)	8	8	8

Applications:

Disinfectant mouth rinses; Antiseptic skin cleansers and surgical scrubs; Pre and post operative antiseptic skin cleansers; Antiseptic powders and ointments for treatment of minor cuts and abrasions; Anti-dandruff shampoos; Control of skin infections and ulcers; Antiseptic vaginal gels, suppositories and douches; Broad antiseptic veterinarian applications such as: teat dips, prevention of local infections and surgical preparations; Treatment of bacterial and fungal infections in fish breeding farms and minimizing infection of fish eggs; Disinfecting wipes for equipment and apparatus treatment.





Polymers for Personal and Oral Care



PVP/H₂O₂

Trade Name: WhiVidone®

Chemical description: Vinylpyrrolidone polymer complex with hydrogen peroxide, PVP/H₂O₂ Complexes;

WhiVidone® 30: complex of KoVidone® K30 & H₂O₂



WhiVidone® 90: complex of KoVidone® K90 & H₂O₂

WhiVidone® XL: complex of PolyKoVidone® XL & H₂O₂

CAS NO.: 9003-39-8, 7722-84-1

Properties:

Polymer complexes retain most of the properties of the parent KoVidone® polymers; Safe and stable form of hydrogen peroxide; Films rapidly release hydrogen peroxide on contact with water or saliva; Can be easily formulated as gels, liquids, tablets and films without taste or odor.



Specification:

WhiVidone®	30	90	XL
Appearance @ 25°C	Free-flowing white powder		
Identification	Conforms to standard		
Hydrogen peroxide (weight %)	17.0-20.0	16.0-20.0	16.0-20.0
Moisture (calculated as % total volatiles - % hydrogen peroxide) % max	5	7	5
Nitrogen content (%)	8--12	8--12	7--12
Heavy metals (includes only As, Hg & Pb, AES-ICP) ppm max	10	10	10

Application:

Tooth whitening/bleaching; Stain removal/bleaching agents for denture cleanser tablets; Contact lens cleaners; Wart treatment; Canker sore treatments; Topical antiseptics: Wound cleaners; Ear wax removers.

Boai NKY

Your Trusted Partner

- Uncompromised product quality.
- Highest quality management system.
- Multiple international quality audits and certifications.
- State of the art manufacturing facility.
- Global warehousing and distribution centers.
- Dedicated customer and technical service.
- Strong customer partnering.



kosher certificate



ISO9001



ISO14001-2004 certificate-Production




ISO18001-2007 Certificate-Export



EXCiPACT Certification



BOAI NKY PHARMACEUTICALS LTD.



Head Office

1888 Wenhua Road Boai, Jiaozuo
Henan, China 454450
Tel: +86-391-8696320
Fax: +86-391-8692950
Email: sales@boai-nky.com

International Business

1708-1710 Huijin Center
#65 Dagu-Bei Road, Financial Street(Huijin) Center
Heping District Tianjin 300020 P.R. China
Tel: +86-22-58316066
Fax: +86-22-58316068
Email: sales@boai-nky.com

Technical Research Center

2-C-7, 13 ZiYuan Road
Huayuan Hightech Industrial Park Nankai District
Tianjin, China 300384
Tel: +86-22-87176799
Fax: +86-22-23771679
Email: tech@boai-nky.com

European Branch

Boa NKY Chemicals GmbH
Paul-Finger Str.15
D-50858 Cologne,
Germany
Tel: +49-221-4680732
Fax: +49-221-2828408
Email: w.kindermann@boai-chemicals.de

Japan Representative Office

5F Shobundo BLDG, Akasaka, Tokyo 107-0052
Tel: +81 3 6441 0865
Fax: +81 3 64410864
E-mail: aiichiro-kumagai@itc-jp.com